

SPATORELLA RED



DESCRIPTION

Smoothing coating to achieve smooth finishes.

CARACTERISTICS

- Smoothing coating, consisting of white cement, white marble powder, resins and special additives.
- Characterized by maneuverability and easy opening without vertical sliding, thus facilitating application to vertical surfaces.
- Used for indoor and outdoor environments.
- Allows a thickness of 1-3 mm for each layer.
- Easily skimmed with abrasive paper to create a thin and solid layer.
- Complies with EN 998-1 standards

APPLICATION DOMAIN

Material for smoothing walls and ceilings filled with traditional mortar or prepared mortar based on lime-cement. Concrete surfaces. Gypsum cardboard walls and ceilings.

IMPORTANT DATA

- Do not add other components such as cement, lime on the given product.
- It should not be applied to previously painted surfaces.
- It should not be applied to surfaces with plastic coverings.
- It must not be applied at a thickness greater than 5 mm.
- Do not add water after the composition is prepared.
- It must be applied at temperatures from + 5 ° C to + 35 ° C

TECHNICAL DATA

Form	Powder
Color	Red
Life Time - storage	12 months in the original packaging in a dry place
Combustibility	Non- ncombustible
Mixture Ratio	7,5 – 8,0 Liter of water per25 kg of SPATORELLA
Handling Time Application	2-3 hours
Temperature	From +5°C to +35°C
PH of the mixture	12
Thickness per layer	2 mm
Waiting Time before 2 nd Layer	30-40 min
Waiting Time before Rubbing	15-20 min
Waiting Time before Coating	3-4 Weeks

REINFORCEMENT WITH LATEX

To improve adhesion, water impermeability, plasticity, elasticity, mechanical resistance etc. SPATORELLA can be reinforced with the LATEX additive. The mixing ratio is 1: 5 with water.

PREPARATION OF MIXTURE

Mix 15 kg of SPATORELLA with 4.5-5 liters of water using with an electric mixer, small number of rotations until forming a homogeneous mass. It is recommended that the mixture be left to stand for about 5 minutes and mixed again before use.

PREPARATION OF SUPPORT

Before applying the product, the support must be prepared, leveled if there is an imbalance of the stands of more than 3 mm. The support must be level, stable, clean, without the presence of paints, varnishes, greases, etc. It must be sprayed before applying the product

APPLICATION OF THE PRODUCT

Spread the product on the surface with a smooth spatula to ensure distribution and complete coverage of the surface. The product is applied from one to two coats to a thickness of up to 3 mm.

CLEANING

Cleaning of work tools and hands should be done when the product is completely dry.

PACKAGING

BAGS OF 25Kg.

